

EUROPEAN PATENT OFFICE

Patent Abstracts of Japan

PUBLICATION NUMBER : 07165455
PUBLICATION DATE : 27-06-95

APPLICATION DATE : 12-09-94
APPLICATION NUMBER : 06217015

APPLICANT : SEKISUI CHEM CO LTD;

INVENTOR : KAMIYA MASATAKE;

INT.CL : C04B 28/26 C04B 7/26 C04B 7/32 C04B 12/04 //(C04B 28/26 , C04B 22:06 ,
C04B 18:08 , C04B 22:08 , C04B 14:10) C04B11:28

TITLE : CURABLE INORGANIC COMPOSITION

ABSTRACT : PURPOSE: To obtain a curable inorganic composition having high strength and excellent durability such as heat-resistance and weather resistance in a short time by compounding prescribed reactive inorganic powder with an alkali metal silicate and water.

CONSTITUTION: This curable inorganic composition is produced by compounding (A) 100 pts.wt. of reactive inorganic powder obtained by compounding (a) 20-99.5wt.% of one or more kinds of inorganic powder selected from fly ash containing ≥ 80 wt.% of powder having particle diameter of $\leq 20\mu\text{m}$, fly ash baked at 400-1000°C and containing ≥ 80 wt.% of powder having particle diameter of $\leq 20\mu\text{m}$ and inorganic powder produced by applying mechanical energy of 0.1-30Kwh/kg to clay with (b) 0.5-80wt.% of one or more kinds of alumina powder selected from alumina cement powder, γ -alumina powder and alumina powder produced by flame-spraying with (B) 1-300 pts.wt. of an alkali metal silicate and (C) 10-1,000 pts.wt. of water.

COPYRIGHT: (C)1995,JPO

Best Available Copy